

copy of West System 105/206 Epoxy resin slow hardener 6kg



Product attributes:

Weight: 6 kg, 1.2 kg

Product codes:

Reference:

P/118/WS/205R/XX

EAN13: -

UPC: -

Product features:

Properties: For 1kg: 6.5 / 7.5m² on porous surface and 8.5 / 9.5m² on non-porous surface.

Product short description:

West System 105/206 Epoxy resin composed of a base and hardener with slow setting (catalyzes in 5 to 7 hours at 21°C) and low viscosity.

It is suitable for fiberglass, wood, aluminum and steel boats. It is recommended not to apply it below 16°C.

Bucket life at 25°C: 10 to 15 minutes.

Proportions: 5 parts of resin for 1 part of hardener

Hard at surface at 21°C in 5 to 7 hours and hard on the core with maximum resistance (at 21°C) in 5 to 7 days.

Product description:

Product gallery: